



Product Description

WESTLAKE low-density polyethylene EC4056 is a natural low density material with an 80 melt index.

Typical Physical Properties

<u>Property^a</u>	<u>Test^b Method</u>	<u>Typical Value, Units^c</u>
Melt Index (Condition 190°C/2.16 kg)	D 1238	80.0 g/10 min
Density	D 4883	911 kg/m ³ (0.911 g/cm ³)
Tensile Stress @ Break 500 mm/min (20 in./min)	D 638 Type IV	8.3 MPa (1200 psi)
Elongation @ Break 500 mm/min (20 in./min)	D 638 Type IV	120%
Flexural Modulus (2% Secant) 12.7 mm/min (0.5 in./min)	D 790	138 MPa (20,000 psi)

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

Applications

WESTLAKE low-density polyethylene EC4056 is a natural low density material with an 80 melt index.

FDA

This product has some 21 CFR clearances. Please contact Westlake Product Regulatory Department for statements.

General

Where required, specimens are compression molded according to ASTM D1928.

Comments

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given.

Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.