



Westlake Chemical

EF796

EF796AA = E6838-796F

Application/Uses

- Disposable diaper film
- Food-contact applications
- Industrial packaging

Product Description

Westlake Polyethylene EF796 is a low density formulation suggested for film applications requiring a good balance of properties such as converter film for industrial packaging and general-purpose packaging.

Typical Physical Properties

<u>Property^a</u>		<u>Test^b Method</u>	<u>Typical Value, Units^c</u>
Melt Index (Condition 190°C/2.16 kg)		D 1238	2.5 g/10 min
Density		D 4883	921 kg/m ³ (0.921 g/cm ³)
Vicat Softening Temperature		D 1525	94°C (201°F)
Haze		D 1003	6%
Gloss @ 45°		D 2457	70
Dart Impact		D 1709A	100 g
Tensile Strength @ Break	M.D.	D 882	26 MPa (3800 psi)
	T.D.	D 882	19 MPa (2700 psi)
Tensile Modulus, 1% Secant	M.D.	D 882	186 MPa (27000 psi)
	T.D.	D 882	220 MPa (32000 psi)
Elongation @ Break	M.D.	D 882	250%
	T.D.	D 882	750%

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

NOTES

Test specimens for blown film: nominal thickness 1.5 mils; blow up ratio 2.4:1, die gap 50 mils.

FDA

This resin grade complies with 21 CFR 177.1520. For further information, please contact Product Regulatory Compliance.

PROCESSING

Melt temperatures of 360° F – 380° F are recommended for Westlake Chemical EF796 with blow-up ratios of 2.4:1 or higher.

COMMENTS

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given.

Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

WESTLAKE CHEMICAL CORPORATION
2801 Post Oak Blvd Suite 600 Houston, Texas
Customer Service: 1-800-545-9577