



Westlake Polymers

Enhancing your life every day

EMAC[®] SP2207

Application/Uses

- Films & Extrusion Coatings
- Flexible Packaging
- Disposable gloves
- Heat Seal Layers
- Tubing
- Tie Layers

Attributes

- Good adhesion or compatibility to various substrates
- Good heat & RF sealing
- Low temperature toughness
- Soft, flexible, tough without plasticizers

Product Description

Westlake EMAC[®] SP2207 is a 20% ethylene methyl acrylate (EMA) copolymer designed for extrusion coating, tie-layers, and extrusions where flexibility, compatibility, low heat seal temperatures, or high coefficient of friction are required. SP2207 provides excellent adhesion to polyolefins, polyesters, and other polymers while providing outstanding low temperature performance.

Typical Physical Properties

<u>Property^a</u>	<u>Test^b Method</u>	<u>Typical Value, Units^c</u>
Melt Index (Condition 190°C/2.16 kg)	D 1238	6.0 g/10 min
Density	D 1505	941 kg/m ³ (0.941 g/cm ³)
Methyl Acrylate Content	Westlake	20%
Vicat Softening Temperature	D 1525	51°C (124°F)
Melting Point by DSC Tm	D 3418	84°C (183°F)
Crystallization Point by DSC Tc	D 3418	67°C (153°F)
Brittleness Temperature	D 746	<-73°C (<-99°F)
Durometer Hardness Shore D Scale	D 2240	39
Tensile Stress @ Break 500 mm/min (20 in./min)	D 638 Type IV Specimen	8.9 MPa (1275 psi)
Elongation @ Break 500 mm/min (20 in./min)	D 638 Type IV Specimen	600%

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

NOTES

EMAC[®] resins adhere to and are compatible with a wide range of materials including paper, polyolefins, oriented polyolefins, polyesters, ionomers, PVC, unplasticized PVC and other polar polymers. For use as heat seal layer, adhesive layer, or modifier for cost/performance enhancement. They are soft, pliable and tough at ambient and freezing temperatures and exhibit excellent ESCR. These polymers exhibit high solids fillability and compatibility with a wide range of polymers. This facilitates their uses as bases for all-purpose concentrates for addition to a wide spectrum of polymers. They process like LDPE.

FDA

This product has some 21 CFR clearances. Please contact Westlake Product Regulatory Department for statements.

PROCESSING

Processing conditions for EMAC[®] and EBAC[®] resins will vary depending on application, fabrication equipment, and other resin use. For assistance with applications and temperature profiles, contact the Westlake Technical Services Department at 903-242-7693.

COMMENTS

Properties reported here are nominal values. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given.

Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

WESTLAKE CHEMICAL CORPORATION
2801 Post Oak Blvd Suite 600 Houston, Texas
Customer Service: 1-800-545-9577